

Alloy	Co	Cr	Ni	Mo	Others
TMP21	Balance	28	2.5	5.5	Si, Fe, C, Mn
Powder Type:	Gas Atomized				
Particles Sizes Available:	-53/+15µm, -106/+45µm, and others upon request				
Typical Hardness:	25-38 HRC				
Apparent Density:	4.98g/cm ³				
Flow Rate:	13.8s/50g				

Application:

- Ball and gate valves
- Valve seats
- Seal rings
- Other erosion and abrasion wear applications

Process:

- 3D Printing

Hazards:

Observe safe practices.

See TMetal material safety data sheet for details.

Standard Sizes & Packaging:**Particle Size**

-53/+15µm,
-106/+45µm

And others upon request

Packaging

5kg/ bottle

Product Overview

TMP21 consists of CoCrMo alloy matrix with solid solution strength. It can be processed by PTA, HVOF, and Laser cladding. TMP21 can retain its properties at high temperatures and is known as its excellent cavitation, galling and metal-to-metal sliding wear resistance. However, it's not recommended for severe hard particle abrasion.

Contact: tmetal.com/contact

