TMP32





Alloy	Со	Cr	W	С	Ni	Others
TMP32	Balance	26	12	1.7	22.5	Si, Fe, Mo
Powder Type:	Gas Atomized					
Particles Sizes Available:	-53/+15μm, and others upon request					
Typical Hardness:	40-45 HRC					
Apparent Density:	-					
Flow Rate:	-					

Application:	Process:

- Valve seats
- Cutting blades
- Seal rings
- Other erosion and abrasion wear applications

•	3D	Printing

Hazards:	Standard Sizes & F	Standard Sizes & Packaging:	
Observe safe practices.	Particle Size	Packaging	
See TMetal material safety data sheet for details.	-53/+15μm	5kg/ bottle	
	And others upon i	And others upon request	

Product Overview

TMP32 was originally designed for the hardfacing of internal combustion engine valves to offer enhanced resistance to corrosion and erosion.

Contact: tmetal.com/contact

