

TMPSF6

Aug 2025



Alloy	Co	Cr	W	C	Ni	Others
TMPSF6	Balance	19	7.5	0.7	13	Si, B
Powder Type:	Gas Atomized					
Particles Sizes Available:	-53/+10µm, -45/+10µm, and others upon request					
Typical Hardness:	45 HRC					
Apparent Density:	-					
Flow Rate:	-					

Application:

- Valve seats
- Cutting blades
- Seal rings
- Other erosion and abrasion wear applications

Process:

- HVOF (High-Velocity Oxy-Fuel Spray)

Hazards:

Observe safe practices.

See TMetal material safety data sheet for details.

Standard Sizes & Packaging:**Particle Size**

-53/+10µm,
-45/+10µm

And others upon request

Packaging

5kg/ bottle

Contact: tmetal.com/contact



Toronto Canada

contact@tmetal.com | 45A West Wilmot Street, Richmond Hill, ON, L4B 2P3, Canada