

Alloy	Co	Cr	W	C	Ni	Others
UMetal	Balance	26	2	0.06	9	Si, Fe, Mo
Powder Type:	Gas Atomized					
Particles Sizes Available:	-150/+45µm, -180/+53µm, and others upon request					
Typical Hardness:	20-45 HRC					
Apparent Density:	-					
Flow Rate:	-					

Application:

- Valve seats
- Cutting blades
- Seal rings
- Other erosion and abrasion wear applications

Process:

- PTA (Plasma Transferred Arc)
- Laser Cladding
- HVOF (High-Velocity Oxy-Fuel Spray)

Hazards:

Observe safe practices.

See TMetal material safety data sheet for details.

Standard Sizes & Packaging:**Particle Size**

-150/+45µm,
-180/+53µm

And others upon request

Packaging

5kg/ bottle

Contact: tmetal.com/contact

