TMPN55A





Alloy	Ni	Cr	Fe	Others	
TMPN55A	Balance	15	14	Si, B, C, Cu, Mo	
Powder Type:	Gas Atomized				
Particles Sizes Available:	-150/+45μm, -180/+53μm, and others upon request				
Typical Hardness:	45 HRC				
Apparent Density:	-				
Flow Rate:	-				

Application: Process:

- Petrochemical valves
- Plastic screws
- Oil pump plungers

PTA (Plasma Transferred Arc)

Hazards:	Standard Sizes & Packaging:		
Observe safe practices.	Particle Size	Packaging	
See TMetal material safety data sheet for details.	-150/+45μm, -180/+53μm	5kg/ bottle	
	And others upon request		

Contact: tmetal.com/contact

