

TMPN62A

Aug 2025



Alloy	Ni	Cr	Fe	Others
TMPN62A	Balance	16	14	Si, B, C, W
Powder Type:	Gas Atomized			
Particles Sizes Available:	-150/+45µm, -180/+53µm, and others upon request			
Typical Hardness:	62 HRC			
Apparent Density:	-			
Flow Rate:	-			

Application:

- Agricultural machine
- plastic screw

Process:

- PTA (Plasma Transferred Arc)

Hazards:

Observe safe practices.

See TMetal material safety data sheet for details.

Standard Sizes & Packaging:**Particle Size**

-150/+45µm,
-180/+53µm

And others upon request

Packaging

5kg/ bottle

Contact: tmetal.com/contact



Toronto Canada

contact@tmetal.com | 45A West Wilmot Street, Richmond Hill, ON, L4B 2P3, Canada