TMPN65A





Alloy	Ni	Cr	Fe	Others	
TMPN65A	Balance	16	15	Si, B, C, W	
Powder Type:	Gas Atomized				
Particles Sizes Available:	-150/+45μm, -180/+53μm, and others upon request				
Typical Hardness:	62 HRC				
Apparent Density:	-				
Flow Rate:	-				

and the second s	
Application:	Process:
Application.	FIUCESS.

- Plastic screw
- oil pump plunger

■ PTA (Plasma Transferred Arc)

Hazards:	Standard Sizes & F	Standard Sizes & Packaging:		
Observe safe practices.	Particle Size	Packaging		
See TMetal material safety data sheet for details.	-150/+45μm, -180/+53μm	5kg/ bottle		
	And others upon request			

Contact: tmetal.com/contact

